


Phase Change Materials (PCM) are hydrated salts that have large amount of heat energy stored in the form of Latent Heat which is absorbed or released when the materials change state from solid to liquid or liquid to solid. The PCM retains its latent heat without any change in physical or chemical properties over thousands of cycles. Various specific temperature PCM's are commercially available in the market (varying between -35°C to 90°C) depending upon the applications.

Technical Specification:

Description : Mixture of Inorganic salts
 Appearance : Light White/Grey coloured liquid



A 30g sample is taken in a test tube in molten condition and placed in a temperature controlled bath. A temperature sensor is placed in the test tube and bath to record the temperatures using a datalogger. The bath is maintained at -36°C during the freezing cycle and at around -15°C during the melting cycle.

Property	Value	Test Method	Test Conditions (if any)
Melting Temp. ($^{\circ}\text{C}$)	-25.6	T - History	@ -15°C (maximum) Bath
Freezing Temp. ($^{\circ}\text{C}$)	-26.2	T - History	@ -36°C Bath
Liquid Density (kg/m^3)	1200	ASTM D891-95	@ 25°C
Latent Heat (kJ/kg)	205	Calorimeter	solid PCM taken at -36°C
Specific Heat-Liquid ($\text{kcal}/\text{kg.K}$)	0.85	Calorimeter	@ 25°C
Base Material	Inorganic chemical	-	-
Congruent Melting	Yes	-	-
Sub Cooling	No	T-History	-
Flammability	No	-	-
Thermal Stability (cycles)	~*	Internal	-
Max. Operating Temp. ($^{\circ}\text{C}$)	~50	-	-

* - Cycling under progress



RGEES LLC, 1465 Sand Hill Road, Candler, NC 28715 United States of America
 Tel: +1.828.708.7178; +1.828.708.7179
 Email: info@rgees.com Website: www.rgees.com